

इंटरनेट

मानक

### Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 8368 (2010): Tungsten Carbide Powder for Hardmetals [MTD  
25: Powder Metallurgical Materials and Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”



BLANK PAGE



भारतीय मानक  
कठोर धातुओं के लिए टंगस्टन कार्बाइड पाउडर — विशिष्टि  
( दूसरा पुनरीक्षण )

*Indian Standard*  
TUNGSTEN CARBIDE POWDER FOR  
HARDMETALS — SPECIFICATION  
( *Second Revision* )

ICS 77.160

© BIS 2010  
**BUREAU OF INDIAN STANDARDS**  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

## FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Powder Metallurgical Materials and Products Sectional Committee had been approved by the Metallurgical Engineering Division Council.

This standard was first published in 1977 and subsequently revised in 1985. In this revision following modifications have been made:

- a) A new clause giving latest reference has been incorporated,
- b) Reference to terminology and method of chemical analysis has been added, and
- c) Requirements of test certificate has been added.

Tungsten carbide powder is used in the manufacture of hardmetals, which find applications in cutting tool tips, rock drilling bits, wear part and dies.

This standard contain clauses **5.3** and **6** which call for agreement between the purchaser and the manufacturer.

For the purpose of deciding whether a particular requirement of this standard is complied with the final value, observed or calculated expressing the results of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

# Indian Standard

## TUNGSTEN CARBIDE POWDER FOR HARDMETALS — SPECIFICATION

( *Second Revision* )

### 1 SCOPE

This standard specifies the requirements of tungsten carbide powder used for the manufacture of hardmetals.

### 2 REFERENCES

The following Indian Standards contain provisions, which through reference in this text, constitute provisions of this standard. At the time of the publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below:

<i>IS No.</i>	<i>Title</i>
1387 : 1993	General requirements for the supply of metallurgical materials ( <i>second revision</i> )
5432 : 1982	Glossary of terms relating to powder metallurgy ( <i>first revision</i> )
6492 : 1972	Methods for sampling of powders for powder metallurgical purposes
7512 : 2006	Method for the determination of average particle size of metal powders by Fisher sub-sieve sizer ( <i>first revision</i> )
12473	Chemical analysis of hardmetals by flame atomic absorption spectrometry:
(Part 1) : 1988	General requirements
(Part 2) : 1988	Determination of calcium, potassium, magnesium and sodium in contents from 0.001 to 0.02 percent ( <i>m/m</i> )
(Part 3) : 1988	Determination of cobalt, iron manganese and nickel in contents from 0.01 to 0.5 percent ( <i>m/m</i> )
(Part 4) : 1988	Determination of molybdenum, titanium and vanadium in contents from 0.01 to 0.5 percent ( <i>m/m</i> )
(Part 5) : 1988	Determination of cobalt, iron, manganese, molybdenum, nickel, titanium and vanadium in contents from 0.5 to 2 percent ( <i>m/m</i> )

### *IS No.*

### *Title*

(Part 6) : 1988	Determination of chromium in contents from 0.01 to 2 percent ( <i>m/m</i> )
12539 : 1988	Determination of total carbon in hardmetals by gravimetric method
12548 : 1988	Determination of insoluble (free) carbon in hardmetals by gravimetric method

### 3 TERMINOLOGY

For the purpose of this standard, definitions as given in IS 5432 shall apply.

### 4 SUPPLY OF MATERIAL

General requirements relating to the supply of tungsten carbide powder shall be as laid down in IS 1387.

### 5 CHEMICAL COMPOSITION

5.1 Chemical composition of tungsten carbide powder shall be as given in Table 1.

**Table 1 Chemical Composition of Tungsten Carbide Powder**

SI No. (1)	Constituent (2)	Percent (3)
i)	Aluminium	0.003, <i>Max</i>
ii)	Calcium	0.005, <i>Max</i>
iii)	Carbon (total)	6.1, <i>Min</i>
iv)	Carbon (free)	0.1, <i>Max</i>
v)	Chromium	0.01, <i>Max</i>
vi)	Cobalt	0.05, <i>Max</i>
vii)	Copper	0.01, <i>Max</i>
viii)	Iron	0.05, <i>Max</i>
ix)	Molybdenum	0.1, <i>Max</i>
x)	Nickel	0.01, <i>Max</i>
xi)	Oxygen	0.08, <i>Max</i>
xii)	Silicon	0.005, <i>Max</i>
xiii)	Sodium+Potassium	0.002, <i>Max</i>
xiv)	Sulphur	0.002, <i>Max</i>
xv)	Phosphorous	0.1, <i>Max</i>
xvi)	Tungsten	Balance

**5.2** The chemical composition of tungsten carbide powder shall be done by the method specified in IS 12473 (Parts 1 to 6), IS 12539 and IS 12548 or any other established instrument/chemical method as agreed to between the purchaser and the manufacturer.

**5.3** The method of chemical analysis of elements in tungsten carbide powder, if Indian Standard not available, shall be agreed to between the purchaser and the manufacturer.

## **6 AVERAGE PARTICLE SIZE**

The average particle size of tungsten carbide powder shall be determined in accordance with IS 7512. The particle size shall be as agreed to between the purchaser and the manufacturer.

## **7 SAMPLING**

The sampling of powder for conducting chemical analysis and particle size determination shall be done in accordance with IS 6492.

## **8 PACKING**

The powder shall be supplied, packed in suitable containers in quantity mutually agreed to between the purchaser and the manufacturer.

## **9 MARKING**

**9.1** Each container of tungsten carbide powder shall be marked with the following information:

- a) Tungsten carbide powder;
- b) Average particle size;
- c) Batch number and/or date of manufacture of powder;
- d) Net mass of powder in the container; and
- e) Manufacturer's name and address.

### **9.2 BIS Certification Marking**

Each container of the tungsten carbide powder may also be marked with the Standard Mark.

**9.2.1** The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of the Standard Mark may be granted to manufacturers or producers, may be obtained from the Bureau of Indian Standards.

## **10 TEST CERTIFICATE**

If required, a test certificate may be supplied with a consignment of tungsten carbide powder indicating details of batch number, chemical composition and average particle size.



## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

## Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

## Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards : Monthly Additions'.

This Indian Standard has been developed from Doc No.: MTD 25 (4817).

### Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

## BUREAU OF INDIAN STANDARDS

### Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: [www.bis.org.in](http://www.bis.org.in)

### Regional Offices:

Telephones

Central	: Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{ 2323 7617 2323 3841
Eastern	: 1/14 C. I. T. Scheme VI M, V. I. P. Road, Kankurgachi KOLKATA 700054	{ 2337 8499, 2337 8561 2337 8626, 2337 9120
Northern	: SCO 335-336, Sector 34-A, CHANDIGARH 160022	{ 260 3843 260 9285
Southern	: C. I. T. Campus, IV Cross Road, CHENNAI 600113	{ 2254 1216, 2254 1442 2254 2519, 2254 2315
Western	: Manakalaya, E9 MIDC, Marol, Andheri (East) MUMBAI 400093	{ 2832 9295, 2832 7858 2832 7891, 2832 7892

**Branches:** AHMEDABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. DEHRADUN. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR. PARWANOO. PATNA. PUNE. RAJKOT. THIRUVANANTHAPURAM. VISAKHAPATNAM.